



# PRODUCT TESTING SERVICE

100 Clemson Research Blvd. Anderson, SC 29625 Tel (864) 646-TILE Fax (864) 646-2821  
TCNA TEST REPORT NUMBER: TCNA-202-06 PAGE: 1 OF 1

**TEST REQUESTED BY:** Florim Ceramiche SpA  
Attn: Allesandro Villa  
Via Canaletto 24  
41042 Fiorano (MO)  
Italy

**TEST SUBJECT MATERIAL:** Identified by client as: Rex – Abisko Mogano 10 x 45

**TEST DATE:** 10/11/06-10/12/06


**TEST PROCEDURE:** ASTM C1028: "Standard Test Method for Determining the Static Coefficient of Friction of Ceramic Tile and Other Like Surfaces by the Horizontal Dynamometer Pull-Meter Method"  
-A Chatillon DFIS 100 digital force gauge was used to measure each pull in pounds-force.  
-A 3 x 3 x 1/8 inch piece of Neolite was used as the sensor.  
-Internal calibration used in lieu of dry calibration factor.

**TEST RESULTS:** The average static coefficient of friction of four (4) pulls on each tile was as follows:

	<u>As Received</u>	<u>After Cleaning</u>
Tile 1: <u>Dry:</u>	<u>0.76</u>	<u>0.79</u>
<u>Wet:</u>	<u>0.62</u>	<u>0.59</u>
Tile 2: <u>Dry:</u>	<u>0.78</u>	<u>0.80</u>
<u>Wet:</u>	<u>0.62</u>	<u>0.64</u>
Tile 3: <u>Dry:</u>	<u>0.84</u>	<u>0.85</u>
<u>Wet:</u>	<u>0.65</u>	<u>0.65</u>

The average static coefficient of friction of twelve (12) pulls was as follows:

<u>Dry:</u>	<u>0.79</u>	<u>0.81</u>
<u>Wet:</u>	<u>0.63</u>	<u>0.63</u>

  
\_\_\_\_\_  
Virgil Irick  
Director of Laboratory Services

10/13/06  
\_\_\_\_\_  
Date